



MASONRY MORTAR MIX

MASONRY MORTAR MIX FOR THE TRADE.

COMPLIES WITH NZS 4210; 1989 FOR MASONRY CONSTRUCTION.



20kg & 30kg

APPLICATION:

Empty contents into a wheelbarrow, mechanical mixer or onto a smooth non-porous surface. Add water gradually, mixing thoroughly until a smooth mix is achieved. Do not over mix. Under ideal conditions a bag of 20kg would require approx 3 - 3.3 litres of water. Damp the clay bricks before laying them. Concrete blocks should be laid relatively dry. Place a layer 15 - 20 mm of mortar between layers of bricks / blocks. The joint gaps are usually 10 - 15mm. Pointing is easier after the mortar has initially set.

DESCRIPTION:

Cemix® Masonry Mortar Mix is for professional trade brick and block mortar jobs. It is ideal for all types of masonry work. The mortar displays a high level of workability and coverage, especially suited for the professional brick/block layers.

TYPICAL APPLICATION/USES:

It is generally used for:

- Brick and block mortar jointing
- Stone and rock walls
- Paving bedding
- Minor plastering repairs

ADVANTAGES:

- No additives required.
- High quality masonry mortar.
- Contains carefully graded and processed sand fractions.
- Exhibits ideal water demand and high workability.
- A hi-tech blend of admixtures guarantees great results.

SUBSTRATE PREPARATION:

Dampen the clay bricks before laying them. Concrete blocks should be laid relatively dry.

MATERIALS:

Cemix® Masonry Mortar Mix consists of a uniformly blended, properly proportioned mixture of sands, Portland cement and other admixtures approved for use in mortar to improve workability and performance of the product.

PRECAUTION:

Hazardous – Portland and blended cement. This product may contain Crystalline Silica. Cements may cause respiratory, skin and eye irritation. Wet cement can be irritating and corrosive to eyes and skin; and may cause skin sensitization (Dermatitis). Repeated inhalation may cause bronchitis, silicosis and lung cancer and increase risk of scleroderma.

CEMIX LTD
19 ALFRED STREET
ONEHUNGA 1061
AUCKLAND
NEW ZEALAND

0800 ASK CEMIX
WWW.CEMIX.CO.NZ



TECHNICAL DATA:

Complies with NZS 4210; 1989 for
Masonry Construction.

COVERAGE:

Under ideal conditions, one 20kg bag is enough
to lay 30 clay bricks and 16 concrete blocks.

PACKAGING:

Cemix® Masonry Mortar Mix is available in 20kg and
30kg bags.

STORAGE & SHELF LIFE:

Cemix® Masonry Mortar Mix in a cool dry area
and use within six (6) months.

CLEANING:

Clean all tools with water & brush immediately
after use.

SAFETY:

Avoid contact with eyes & do not ingest.

First Aid

Irrigate eyes plenty of water & seek medical advice immediately

SPILLS AND LEAKS:

Keep out of sewers & storm water drains & dispose of any leftover material as trade
waste in accordance with local authority guidelines.

DISCLAIMER:

Please Note: Recommendations and advice regarding the use of this product are
to be taken as a guide only. Other than as appears on this products packaging,
Cemix® LTD. does not give any warranty express or implied as to the suitability of
this product for your particular use, because the usage of this product is beyond the
control of Cemix® LTD. If you need advice concerning the use of suitability of this
product for your particular application, please contact Cemix® LTD first. If this product
is defective because of Cemix® LTD's fault, please contact the supplier or Cemix®
LTD. who will replace it at no cost.

CEMIX LTD
19 ALFRED STREET
ONEHUNGA 1061
AUCKLAND
NEW ZEALAND
0800 ASK CEMIX
WWW.CEMIX.CO.NZ

